

MOHM CHEMICAL SDN. BHD. (Co.No.276851-U) MCX MARKETING SDN. BHD. (Co.No.363532-T)

H.Q.: No. 32, Jalan Temenggong, Off Jalan Tampoi, 81100 Johor Bahru, Johor. Malaysia.

Tel: (60 7) 333 1222 Fax: (60 7) 332 0545 / 333 7919

Branch: No. 43, Jalan Tambur 33/19, Sek. 33, Shah Alam Technology Park,

47100 Shah Alam, Selangor. Malaysia.

Tel: (60 3) 5124 0876 / 5124 0878 Fax: (60 3) 5124 0877

Email: info@mochem.com Website: www.mochem.com / www.xtraseal.com



REV : 01

DATE : 12th Oct 2012

TECHNICAL DATA SHEET

X'traseal® SA-103 MULTIPURPOSE RTV ACETOXY SILICONE SEALANT

DESCRIPTION:

X'traseal°SA-103 MULTIPURPOSE SILICONE SEALANT IS ONE PART SEALANT THAT OFFER EXCELLENT ADHESION, WEATHERABILITY AND ELASTICITY FOR GENERAL GLAZING AND FOR SEALING APPLICATION.

FEATURES:

- ♦ ACETIC ACID CURING SYSTEM
- OUTSTANDING DURABILITY
- ♦ ONE PART NO MIXING
- **♦** PERMANENTLY FLEXIBLE
- ♦ EXCELLENT GUNNABILITY (-20°C TO 50°C)
- ♦ WEATHER PROOF
- ♦ LOW SHRINKAGE
- ♦ NO SAGGING
- ♦ PRIMERLESS ADHESION TO MOST MATERIALS
- ♦ UV RESISTANCE

USES:

- ♦ GENERAL GLAZING: GLASS, PLASTIC, CHANNEL OR STOP.
- ◆ CURTAINWALL SEALING: GLASS, STEEL, GRANITE AND PLASTIC.
- ◆ GENERAL SEALING: SHEET METAL, SKYLIGHTS, VENTILATORS, AIR-CONDITIONING.

WE RECOMMEND PRELIMINARY COMPATIBILTY TESTS PRIOR TO APPLICATION TO ACHIEVE DESIRABLE RESULTS

NOT RECOMMENDED FOR:

SA-103 IS AN ACETIC ACID CURING SILICONE AND IS NOT SUITABLE WHERE THE ACETIC ACID COMPONENT WILL CORRODE THE BASE MATERIAL.

NOT FOR: TRAFFIC AREAS OR AREAS SUBJECT TO ABRASION.

NOT FOR: STRUCTURAL GLAZING.

NOT FOR: ON MARBLE, QUARTZITE OR NATURAL STONES.

JOINT DESIGN:

THE SPECIFIED SEALANT BEAD SIZE SHOULD BE CALCULATED TO COMPLY WITH THE COMPRESSION AND EXTENSION CAPABILITIES OF THE SEALANT IN RELATION TO THE ANTICIPATED JOINT WIDTH DUE TO EXPANSION AND CONTRACTION.

GENERALLY CALCULATION OF THE WIDTH OF S-A3 SEALANT BEAD SHOULD BE COMPUTED ON THE BASIS OF A MAXIMUM $\pm\,20~\%$

COMPRESSION AND EXTENSION CAPABILITY MINIMUM BEAD SIZE SHOULD NOT BE LESS THAN 3mm TO ACCOMMODATE MOVEMENT.DESIGN JOINT DEPTH OF WHICH RATIO WIDTH BECOMES 0.5 TO 1.

SUITABLE JOINT DEPTH VS WIDTH:

6mm x 6mm

8mm x 12mm

10mm x 20mm

- * JOINT SIZE MINIMUM 3mm x 3mm.
- * JOINT SIZE MAXIMUN 30mm.



MOHM CHEMICAL SDN. BHD. (Co.No.276851-U) MCX MARKETING SDN. BHD. (Co.No.363532-T)

H.Q.: No. 32, Jalan Temenggong, Off Jalan Tampoi, 81100 Johor Bahru, Johor. Malaysia.

Tel: (60 7) 333 1222 Fax: (60 7) 332 0545 / 333 7919

Branch: No. 43, Jalan Tambur 33/19, Sek. 33, Shah Alam Technology Park,

47100 Shah Alam, Selangor. Malaysia.

Tel: (60 3) 5124 0876 / 5124 0878 Fax: (60 3) 5124 0877

Email: info@mochem.com Website: www.mochem.com / www.xtraseal.com



REV : 01

DATE : 12th Oct 2012

TECHNICAL DATA SHEET

X'traseal® SA-103 MULTIPURPOSE RTV ACETOXY SILICONE SEALANT

APPLICATION:

- ♦ SURFACE MUST BE CLEAN AND DRY.
- ♦ MASK SMOOTH SURFACE TO SIMPLIFY CLEAN UP.
- ♦ USE APPROVED BACK-UP MATERIAL IN JOINT.
- CUT NOZZLE TO DESIRED SIZE.
- ♦ INSERT CARTRIDGE INTO CAULKING GUN.
- ♦ PUSH SEALANT AHEAD FOR UNIFORM BEAD.
- ♦ TOOL WITHIN 5 MINUTES.
- ◆ CLEAN OFF EXCESS SEALANT WITH M.E.K. OR TOLUENE.

CURING TIME:

SA-103 WILL TACK FREE IN APPROXIMATELY 15 MINUTES AND WILL CURE TO A DEPTH OF 10mm IN 7 DAYS. LONGER CURING TIME MAY BE NECESSARY IN DRY AND LOW HUMIDITY AREA.

SPECIFICATION:

CURING SYSTEM ACETOXY

APPEARANCE NON-SAGGING PASTE

ODOUR VINEGAR SMELL

SPECIFIC GRAVITY 0.97 ± 0.05 SHORE A HARDNESS 15 APPROX.

ELONGATION 300%

TENSILE STRENGTH

TACK FREE TIME

APPLICATION TEMP.

SERVICE TEMP.

SHELF LIFE

1.4MPa APPROX.

1.5 MINUTES

-20°C TO 50°C

-40°C TO 100°C

12 MONTHS

STORAGE:

MATERIAL SHOULD BE STORED IN A DRY AND COOL PLACE BETWEEN +5°C TO +30°C.

CAUTION:

READ AND UNDERSTAND MATERIAL SAFETY DATA SHEET OF THIS PRODUCT BEFORE HANDLING OR USING.

This information is provided in good faith and is believed accurate based on a review of current composition and information supplied by vendors. No warranty is expressed or implied. Liability is expressly disclaimed.